

Chemical Resistance of Garlock GRAPH-LOCK® Gasketing

A general guide for selection of gasketing material, Rev. 4/07

KEY: **A = Suitable**
 B = Depends on operating conditions
 C = Unsuitable
 – = No data or insufficient evidence

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Acetaldehyde (Ethanol)		100	A	A	A	C
Acetate Solvents		100	A	A	A	–
Acetic Acid (Ethanoic Acid)	Cold	Conc.	A	A	A	A
Acetic Acid (Ethanoic Acid)	Cold	Dilute	A	A	A	A
Acetic Acid (Ethanoic Acid)	Hot	Conc.	A	A	A	A (80%, 250F)
Acetic Acid (Ethanoic Acid)	Hot	<15	A	A	A	A (at 250F)
Acetic and Propionic Acid	Cold		A	A	A	–
Acetic Anhydride (Ethanoic Anhydride)	20		A	A	A	C
Acetone, Dry			A	A	A	B
Acetylene Gas			A	A	A	–
Acrylonitrile			A	A	–	A (at 70F)
Air	<400		A	A	A	A
Air	<245		A	A	A	A
Alcohol (Ethyl)			A	A	A	–
Aldehyde			A	A	A	–
Alkanes			A	A	–	–
Alkyl Acetone			A	A	–	–
Alkyl Alcohol			A	A	A	–
Alkyl Amine			A	A	A	–
Alkyl Arylsulphonics			A	A	–	–
Alkyl Benzene			A	A	A	–
Alkyl Chloride			A	A	A	C
Alkylate, Light			A	A	A	–
Alpha Picoline			A	A	–	–
Alum Solution			A	B	A	A (at 150F)
Aluminum Chloride		All	A	B	B	A
Aluminum Hydroxide (Boehmite)			A	A	B	A (at 300F)
Aluminum Sulfate, Aqueous			A	A	A	A
Amine, Fat Condensate			A	A	A	–
Ammonia, Anhydrous	<50		A	A	A	–
Ammonia, Aqua	<50	>10	A	A	B	A
Ammonia, Aqua	<50	<10	A	A	B	A
Ammonia, Gas (dry)			A	A	A	A (at 150F)
Ammonium Bicarbonate (Aqueous)			A	A	A	A (at 130F)
Ammonium Bifluoride			A	B	A	–
Ammonium Bisulfate			A	–	–	–
Ammonium Carbonate			A	A	A	A (at 300F)
Ammonium Chloride (Sal Ammoniac)			A	A	A	A (at 150F)
Ammonium Hydroxide			A	A	A	B
Ammonium Nitrate			A	A	A	A (at 100F)

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:
 Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Ammonium Persulfate			A	B	B	A (at 150F)
Ammonium Phosphate (Mono-Basic)			A	A	A	A (at 100F)
Ammonium Phosphate (Di-Basic)			A	A	A	–
Ammonium Phosphate (Tri-Basic)			A	A	A	–
Ammonium Sulfate (Aqueous)	Any	All	A	A	A	A (at 150F)
Ammonium Thiocyanate		0-63	A	A	–	A (at 70F)
Amyl Acetate			A	A	A	C
Amyl Alcohol			A	A	A	A (at 200F)
Amyl Nitrate			A	A	–	–
Aniline (Aminobenzene)			A	A	A	B
Aniline Hydrochlorine	All	0-60	A	C	C	C
Anti-Freeze (Water, Alcohol, and Glycol)			A	A	A	C
Aqua Regia			C	C	C	C
Argon Gas			A	A	A	–
Arochlor 1248			A	A	A	–
Aromatic Fuels			A	A	A	B
Arsenic Acid, (Ortho)			A	A	A	A
Arsenic Trichloride		100	A	–	–	–
Asphalt			A	A	A	–
Aureomycin		100	A	–	–	–
Barium Carbonate (Sat'd)			A	B	B	A (at 250F)
Barium Chloride (Aqueous)		<20	A	A	A	A (at 250F)
Barium Hydroxide			A	B	B	B
Barium Nitrate (Aqueous)			A	B	–	A (at 170F)
Barium Sulfide (sat'd)			A	B	–	–
Beer			A	A	A	A (at 70F)
Beer Wort			A	A	A	–
Beet Juice			A	A	A	–
Beet Pulp			A	A	A	–
Beet Sugar Solution			A	A	A	A
Benzene (Coal tar product) (Benzol)			A	A	A	B
Benzene Hexachloride		100	A	–	–	–
Benzine (Petroleum Product)			A	A	A	–
Benzoic Acid			A	A	A	A (at 250F)
Benzoic Acid Solution			A	A	A	A
Benzol			A	A	A	–
Benzyl Sulfonic Acid		60	A	–	–	B
Bichloride of Mercury	Amb.		A	–	–	–
Bittern			–	–	–	–
Black Liquor			A	A	B	–
Bleach Solutions			A	A	A	–
Blood			A	A	–	–
Boiler Feed Water			A	A	A	–
Bonderite Solution			A	A	–	–
Borax Sol. (Sodium Tetraborate)			A	A	A	–
Boric Acid	95	50	A	A	A	A (at 200F)
Boric Acid, Aqueous	Any	All	A	A	A	A
Boron Trichloride			A	A	A	–

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:
Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Brine Calcium pH 8			A	A	A	–
Brine, Calcium and Magnesium Chloride)			A	A	A	–
Brine, Calcium and Sodium Chloride			A	A	A	–
Brine, Chloride pH 8			A	A	A	–
Brine, Sea water	<80		A	B	A	A
Brine, Sodium Chloride			A	C	A	–
Bromine (Br2)			C	C	C	C
Bromine, Wet (HBr)			A	C	A	C
Bromo Methane			A	A	–	–
Bunker C Fuel oil			A	A	A	–
Butadiene			A	A	A	B
Butane (LPG)			A	A	A	–
Butanol (Butyl Alcohol)		100	A	A	A	C
Butyl Acetate			A	A	A	A (at 250F)
Butyl Alcohol (Butanol)			A	A	A	C
Butyl Cellosolve		0-100	A	–	–	–
Butyl Phthalate	<48		A	A	A	–
Butylacrylate			A	–	–	–
Butylamine			A	A	A	–
Butylene (Butene) (Ethylethylene)			A	A	A	–
Butyric Acid (Butanic Acid)		100	A	B	A	C
Calcium Bisulfide			A	A	A	–
Calcium Bisulfite		100	A	A	B	C
Calcium Carbonate (Aragonite)			A	A	A	A (at 250F)
Calcium Chlorate (Aqueous)	<60	0-10	A	C	A	–
Calcium Chloride (Wet)			A	B	A	A (at 250F)
Calcium Hydroxide (Aqueous) (Lime Water)			A	A	A	A (at 200F)
Calcium Hypochlorite	<32		A	A	A	A (at 250F)
Calcium Magnesium Chloride			A	A	A	–
Calcium Phosphate			A	A	A	–
Calcium Sulfate			A	B	B	A (at 100F)
Cane Juice			A	A	A	–
Carbolic Acid (Phenol)	Amb.		A	A	A	–
Carbolic Acid (Phenol)	205	All	A	A	A	–
Carbon Bisulfide			A	A	A	C
Carbon Dioxide (Dry)	600		A	A	A	B
Carbon Dioxide (Wet)	600		A	A	A	B
Carbon Disulfide			A	A	A	C
Carbon Monoxide			A	A	A	A (at 200F)
Carbon Tetrachloride (Anhydrous)			A	A	A	C
Carbonate of Soda (Aqueous)			A	A	A	
Carbonic Acid, Aqueous			A	A	A	A (at 150F)
Catsup			A	A	A	–
Caustic (Chloride of Sodium)			A	C	A	–
Caustic Cyanogen			A	A	A	–
Caustic Potash (Aqueous)			A	B	B	–
Caustic Soda (Aqueous)			A	A	A	–
Caustic Strontia (Aqueous)			A	–	–	–

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:
Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Caustic Sulfide			A	-	-	-
Caustic Zinc Chloride (Aqueous)			A	-	-	-
Cellosolve Solvent		0-100	A	-	-	B
Chloral Hydrate			A	-	-	C
Chlorethylbenzene		100	A	-	-	-
Chloride of Lime			A	C	A	-
Chloride of Zinc (Aqueous)			A	-	A	-
Chlorinated Solvents (Dry)			A	A	A	-
Chlorinated Solvents (Wet)			A	A	A	-
Chlorine (Dry)			A	B	A	C
Chlorine (Wet)	<22		A	C	A	C
Chlorine Dioxide	<70		A	-	-	-
Chlorine, Anhydrous Liquid			A	B	C	C
Chloroacetic Acid (Ethyl Chloracetate)			A	C	A	-
Chloroacetone			A	A	-	-
Chlorobenzene			A	A	A	A (at 100F)
Chloroform			A	A	A	A (at 100F)
Chloropicrin			A	A	A	-
Chlorosulfonic Acid	Cool	<50	A	C	A	C
Chrome Alum			A	A	-	-
Chromic Acid, Aqueous	Cool	<90	A	B	A	A (at 200F)
Chromic Oxide (Aqueous)		50	B	-	B	B
Chromium Potassium Sulfate (Aqueous)		10	A	A	-	-
Citric Acid, Aqueous	Hot		A	A	A	A (at 100F)
Cocoa Butter			A	A	A	-
Cocoanut Acid, Fatty			A	A	A	-
Cocoanut Oil			A	A	A	B
Cod Liver Oil			A	A	A	-
Condensate (Water)			A	A	A	A
Copper Acetate (Blue Verdigris)			A	A	A	-
Copper Ammonium Acetate (Aqueous) CAA			A	A	A	-
Copper Chloride			A	C	-	A (at 150F)
Copper Cyanide			A	B	A	-
Copper Nitrate			A	A	B	A (at 150F)
Copper Sulfate (Blue Vitriol) (Aqueous)	Any	All	A	-	-	-
Copper Sulfate (Blue Vitriol) (Aqueous)		10	A	B	A	A (at 150F)
Copper Sulfate (Blue Vitriol) (Aqueous)		50	A	B	A	A (at 150F)
Copperas (Green)			A	-	-	-
Corn Oil			A	A	A	A
Cotton Seed Oil			A	A	A	A (at 150F)
Creosol, Meta			A	A	B	C
Creosote (Coal Tar)			A	A	A	-
Cresylic Acid (Alkyl Phenols)			A	A	A	A (at 200F)
Crude Oil			A	A	A	A (at 150F)
Cupric Chloride	Any	All	A	-	-	A (at 250F)
Cupric Sulfate (Aqueous)			A	A	B	-
Cuprous Ammonia Acetate (Aqueous)			A	A	A	-
Cutting Oil			A	A	A	-

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Cyanide (Aqueous)			A	-	-	-
Cyanogen in Water			A	A	-	-
Cyclohexane (Hexahydrobenzene)			A	A	A	-
Cyclohexanone			A	A	A	A (at 70F)
Cyclohexene ((Tetrahydrobenzene)			A	A	A	-
DDT Solution (Kerosene solvent)			A	A	A	-
DDT Solution (Toluene solvent)			A	A	A	-
De-Butanizer Reflux			A	A	A	-
De-Ethanizer Charge			A	A	A	-
De-Propanizer Reflux			A	A	A	-
Deoxidine		<60	A	-	-	-
Diacetone Alcohol			A	A	A	-
Dibromoethyl Benzene			A	A	A	-
Dibutyl Amine			A	A	A	-
Dibutyl Cellusolve Adipate			A	A	A	-
Dibutyl Phthalate			A	A	-	B
Dibutylether			A	A	A	-
Dichlorobenzene			A	A	A	C
Dichloroethane			A	A	A	B
Dichloropropionic Acid	<170	90-100	A	-	-	-
Diesel Fuel			A	A	A	A (at 150F)
Diethanolamine (DEA)			A	A	A	A (at 250F)
Diethyl Carbonate (Ethyl Carbonate)			A	A	A	-
Diethyl Ether			A	B	B	-
Diethylene			A	-	-	-
Diethylene Glycol			A	A	B	B
Diethylene Glycol Ethyl Ether			A	-	-	-
Diethylene Triamine			A	A	A	-
Di-isobutyl Ketone			A	A	A	-
Di-isopropyl Ketone			A	A	A	-
Dimethyl Amine			A	-	-	C
Dimethyl Formaldehyde			A	A	A	-
Dimethyl Formamide			A	B	-	A (at 167F)
Dimethyl Hydrazine (UDMH)			A	A	A	-
Dimethyl Phthalate			A	-	-	A (at 200F)
Dimethyl Terephthalate			A	A	A	-
Dinitrochlorobenzene (DNCB)			A	A	A	-
Dinitrochlorobenzene and Styrene			A	A	A	-
Dinitrotoluene			A	-	-	-
Diocyl-amine			A	A	A	-
Diocyl Phthalate			A	A	A	B
Dioxane		0-100	A	-	-	A (at 167F)
Diphenyl			A	A	A	C
Dish Water			A	A	A	A
Dow Corning Silicone Fluid			A	A	A	-
Dowtherm A (dry)			A	A	A	-
Dowtherm E (dry)			A	B	A	-
Dye Wood Liquor			A	-	-	-

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar-polyester)
	°C	%				
Ethane (Methylmethane)			A	A	A	–
Ethanol (Ethyl Alcohol)			A	A	A	C
Ethanolamine			A	A	A	–
Ether			A	A	A	–
Ethyl Acetate			A	A	A	C
Ethyl Acrylate			A	A	A	B
Ethyl Alcohol (Ethanol)		100	A	A	A	A (at 167F)
Ethyl Alcohol (Ethanol)		35	A	A	A	A (at 167F)
Ethyl Benzene			A	A	A	C
Ethyl Benzoate			A	–	–	–
Ethyl Cellosolve			A	–	–	–
Ethyl Chloride (Dry) (Chloroethane)			A	A	B	C
Ethyl Chlorocarbonate			A	–	–	–
Ethyl Chloroformate			A	–	–	–
Ethyl Chlorohydrin			A	–	–	–
Ethyl Ether (Ethyl Oxide)			A	B	B	C
Ethyl Formate			A	–	–	–
Ethyl Hexanol			A	–	–	–
Ethyl Pyridine			A	A	A	–
Ethylene (Ethene)			A	A	A	–
Ethylene Chloride (Ethylene Dichloride)			A	A	B	C
Ethylene Chlorohydrin		0-8	A	B	B	C
Ethylene Diamine			A	B	B	–
Ethylene Dibromide		100	A	–	–	–
Ethylene Dichloride (Ethylene Chloride)		100	A	A	B	C
Ethylene Glycol			A	A	A	C
Ethylene Oxide		100	A	A	A	C
Ethylene Oxide and Freon 12		12/80	A	A	A	–
Ethylene Trichloride			A	–	A	–
Ethylene Vinyl Acetate			A	–	–	–
Fatty Acid, Oleic.	95		A	B	A	A (at 150F)
Ferric Chloride (Aqueous)			A	C	A	A (at 200F)
Ferric Nitrate (Sat'd)			A	B	B	–
Ferric Sulfate (Aqueous)			A	A	A	A (at 150F)
Ferrous Chloride (Sat'd)			A	C	B	A (at 200F)
Ferrous Sulfate			A	B	B	A (at 200F)
Fluoboric Acid			A	B	A	B
Fluorine	<149	100	A	A	B	C
Fluorolube			A	A	A	–
Fluosilicic Acid			A	B	C	–
Folic Acid			A	–	–	–
Formaldehyde (Methanol)			A	A	B	B
Formalin		40	A	A	A	–
Formalin R Formaldehyde			A	–	–	–
Formic Acid (Methanoic Acid)	Any	All	A	–	–	A (at 200F)
Formic Acid (Methanoic Acid)	Hot	90	A	B	A	A (at 200F)
Freon 11 and Refrig. Oil			A	A	A	–
Freon 12 and Refrig. Oil			A	A	A	–

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Freon 22 and Refrig. Oil			A	A	A	–
Freon 113 and Refrig. Oil			A	A	A	–
Freon 114 and Refrig. Oil			A	A	A	–
Freon 121 and Refrig. Oil			A	A	A	–
Freon 134			–	–	–	–
Freon, Liquid			A	A	A	–
Fruit Acid			A	A	A	–
Fruit Juices			A	A	A	A
Fuel Oil			A	A	A	A (at 100F)
Fuel Oil, Acidic			A	A	A	–
Fuel Oil #6			A	A	A	–
Furfural			A	A	A	C
Gas Oil			A	A	A	–
Gasoline Aromatic			A	A	A	B
Gasoline 100 and 130 Octane.			A	A	A	B
Gasoline Hi-Test w/Mercaptan, H2S			A	A	A	B
Gelatin			A	A	A	A (at 150F)
Glaubers Salt (Aqueous) (Sodium Sulfate)			A	A	A	–
Glucose			A	A	A	A
Glue			A	A	A	–
Glue Sizing			A	A	A	–
Glycerine (Glycerol)		0-100	A	A	A	A (at 250F)
Glycols			A	A	A	C
Grape Juice			A	A	A	A
Grease			A	A	A	–
Green Sulfate Liquor			A	A	A	–
Helium			A	–	–	–
Heptane			A	A	A	B
Hexachloro Acetone			A	–	–	–
Hexane			A	A	A	B
Hexene (Butylethylene)			A	–	–	–
Hexone			A	A	A	–
Hexyl Alcohol (Hexanol)			A	–	–	–
Hops			A	–	–	–
Hydrazine			A	A	–	–
Hydrobromic Acid			A	C	B	A (at 250F)
Hydrochloric Acid (Hydrogen Chloride)	<50	Conc.	A	C	A	B
Hydrochloric Acid (Hydrogen Chloride)	<50	Dilute	A	C	A	A
Hydrochloric Acid (Hydrogen Chloride)	>50	Conc.	A	C	B	B
Hydrochloric Acid (Hydrogen Chloride)	>50	Dilute	A	C	B	A (at 167F)
Hydrocyanic Acid (Prussic)			A	C	–	A (at 70F)
Hydrofluoric Acid	Cold	<55	A	C	B	A
Hydrofluoric Acid, Aqueous	Any	All	A	–	–	B
Hydrofluoric Acid, Aqueous	Cold	>65	A	C	B	B
Hydrofluosilicic Acid	Any	0-20	–	–	–	–
Hydrogen			A	A	A	A
Hydrogen Fluoride (H F Acid) Anhydrous	Cold	<65	A	C	B	B
Hydrogen Fluoride (H F Acid) Anhydrous	Hot	All	A	C	B	B

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:
Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Hydrogen Fluoride (H F Acid) Anhydrous	Cold	>65	A	C	B	B
Hydrogen Peroxide	Cold	>90	B	B	B	B
Hydrogen Sulfide (Dry)	Cold	>90	B	B	B	B
Hydrogen Sulfide (Dry)	Hot		B	B	B	B
Hydrogen Sulfide (Wet)	Cold		B	B	B	B
Hydrogen Sulfide (Wet)	Hot		B	B	B	B
Hypochlorous Acid			A	C	A	–
Ink			A	B	–	A
Insecticides (Aromatic)			A	B	A	–
Insecticides (Nonaromatic)			A	B	A	–
Iodine	<22	100	A	C	A	C
Iodoform			A	A	A	–
Isobutane			A	A	A	–
Isobutyl Alcohol			A	A	A	–
Isobutyl Methyl Ketone			A	A	A	–
Isobutylene			A	A	A	–
Isodecane			A	–	–	–
Iso-Octane			A	A	A	–
Isopentane			A	A	A	–
Isopropanol			A	A	A	C
Isopropyl Acetate		100	A	A	A	–
Isopropyl Acetone			A	A	A	–
Isopropyl Alcohol		0-100	A	A	A	C
Isopropyl Chloride			A	–	–	–
Isopropyl Ether		100	A	A	A	–
Isopropylamine			A	A	A	–
JP-3			A	A	A	–
JP-4			A	A	A	C
JP-5			A	A	A	C
JP-6			A	A	A	–
JP-X			A	A	A	–
Kerosene		100	A	A	A	C
Lacquer (MEK Solvent)			A	A	A	–
Lactic Acid	Hot	<10	A	C	A	A (at 200F)
Lactic Acid	Any	All	A	–	–	A (at 150F)
Lard (Animal Fat)			A	A	A	A
Latex			A	A	A	–
Lavender Oil			A	A	A	–
Lead, Molten			B	–	–	–
Lead Acetate (Liquid)			A	A	A	A (at 200F)
Lead Nitrate	<22		A	B	B	A (at 100F)
Lead Sulphamate			A	B	B	–
Lime Bleach			A	–	–	–
Lime Water (Calcium Hydroxide)			A	A	A	–
Lindol			A	A	A	–
Linseed Oil			A	A	A	–
Liquid Oxygen			B	B	B	B
Liquid Petroleum Gas (LPG)			A	A	A	–

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Liquor, Lime			A	-	-	-
Liquor, Pulp Mill			A	A	A	-
Liquor, Steep			A	-	-	-
Liquor, Sulfate			A	-	-	-
Lithium Bromide Brine			A	A	A	-
Lithium Chloride (Aqueous)			A	A	A	A (30%, 200F)
Lye, Caustic			A	-	-	-
Lye, Salty			A	-	-	-
Magnesium Carbonate			A	-	-	A (at 70F)
Magnesium Chloride (Bischofite)			A	A	A	A (at 200F)
Magnesium Hydroxide (Brucite)			A	A	A	C
Magnesium, Molten			C	C	C	C
Magnesium Nitrate			B	B	B	B
Magnesium Sulfate (Epsom Salt) (Aqueous)			A	B	B	A (at 100F)
Magnesium Sulfite (Aqueous)			A	-	-	-
Maleic Acid			A	A	A	C
Maleic Anhydride			A	A	A	-
Maleic Hydrazide			A	A	-	-
Manganese Chloride (Aqueous)			A	C	A	-
Manganese Sulfate (Aqueous)			A	A	A	-
Mannitol			A	-	-	-
Marsh Gas (Methane)			A	A	A	-
Marsh, Anti-biotic Fermentation, No solvent			A	A	-	-
Marsh, With Solvent			A	A	A	-
Mayonnaise			A	A	A	-
MEA (Monoethanolamine)			A	A	A	-
MEA- With Copper Sulfate			A	A	A	-
Melamine Resins			B	C	-	-
Mercaptan			A	-	-	-
Mercuric Chloride			A	B	B	A (at 70F)
Mercury			A	A	A	A (at 150F)
Mercury Salts			A	A	A	-
Mercury Vapor			A	A	A	-
Mesityl Oxide (Ketone)			A	A	-	-
Methane (Marsh Gas)			A	A	A	A
Methanol (Methyl Alcohol)			A	A	A	C
Methyl Acetate			A	B	A	C
Methyl Acrylate			A	A	-	-
Methyl Alcohol (Methanol)		0-100	A	A	A	C
Methylamine			A	A	-	-
Methyl Bromide (Bromomethane)			A	A	-	C
Methyl Butyl Ketone			A	A	-	-
Methyl Cellosolve			A	B	-	-
Methyl Chloride (Chloromethane) (Anhydrous)			A	A	-	C
Methyl Chlorosilanes			B	-	-	-
Methyl Cyclopentane			A	-	-	-
Methyl Dichloride			A	A	-	-
Methylene Chloride (Dichloromethane)			A	B	B	C

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:
Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Methylene Dichloride			A	A	-	-
Methyl Ether			A	-	-	-
Methyl Ethyl Ketone (MEK)			A	A	A	A (at 167F)
Methyl Formate			A	-	-	-
Methyl Isobutyl Ketone		100	A	B	A	C
Methyl Isopropyl Ketone			A	A	-	-
Methyl Methacrylate			A	B	-	-
MIL F-25558 (RJ-1)			A	A	A	-
MIL L-7808			A	A	A	-
MIL H-5606 (HFA)			A	A	A	-
MIL H-5606 (J43)			A	A	A	-
MIL O-8515			A	A	A	-
MIL O-8200 (Hydr)			A	A	A	-
Milk			A	A	A	A
Milk of Lime			A	A	A	-
Mine Water	20		A	A	A	-
Mine Water Acid	<20		A	A	A	-
Mineral Spirits			A	A	A	-
Miscella 20% Soya Oil			A	A	A	-
Mixed Sulfuric and Nitric Acid	Any	All	C	C	C	C
Mobiltherm Heat Transfer Fluid		100	A	-	-	-
Molasses			A	A	A	A
Monochloro Acetic Acid		100	A	B	B	-
Monochlorobenzene		100	A	A	A	-
Monoethanolamine (MEA)			A	A	A	-
Monoethylene glycol ethyl ether			A	-	-	-
Monomethyl Amine			A	-	-	-
Monovinyl Acetate			A	-	-	-
MTBE			A	-	-	-
Muriatic Acid (See Hydrochloric acid)			A	C	A	-
Mustard			A	A	A	-
Naphtha			A	A	B	C
Naphtha, Crude			A	A	-	C
Naphthalene			A	A	A	C
Naphthenic Acid	<290	All	A	A	A	-
Natural Gas Liquid			A	A	A	-
Neatsfoot Oil			A	A	A	-
Nickel Acetate			A	-	-	-
Nickel Carbonyl (Ni(CO)4)	<60		A	-	-	-
Nickel Chloride	Any	All	A	-	-	C
Nickel Chloride	Hot	<30	A	B	B	C
Nickel Cobalt Sulfate, 5% H2SO4	95		A	C	-	-
Nickel Nitrate	<48		-	-	-	A
Nickel Salts			A	-	-	-
Nickel Sulfate			A	B	B	A (at 200F)
Nicotine Sulfate			A	A	-	-
Nitric Acid	<85	<10	A	A	A	A
Nitric Acid	<60	10-20	A	A	A	A

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/Applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
	°C	%	3120	3124/3126 3125SS 3125TC	3125HC (H276)	3125MC (Mylar-polyester)
			3123/3125	3128		
Nitric Acid	<38	>20	A	A	A	C
Nitric Acid (Fuming)	Hot		C	C	C	C
Nitrobenzene			A	B	C	C
Nitrobenzine			A	A	-	-
Nitrochloroform			A	A	-	-
Nitroethane			A	A	-	-
Nitrogen Gas			A	A	A	A
Nitromethane			A	A	A	-
Nitropropane			A	A	-	-
Oakite			A	-	-	-
Octyl Alcohol		100	A	-	-	-
Oil & Ammonia			A	A	A	-
Oil, Animal, Bone			A	A	A	-
Oil, Animal, Cod			A	A	A	-
Oil, Animal, Lard			A	A	A	-
Oil, Animal, Menhaden			A	A	A	-
Oil, Animal, Neatsfoot			A	A	A	-
Oil, Animal, Sperm			A	A	A	-
Oil, Animal, Whale			A	A	A	-
Oil, Bunker 'C'			A	A	A	-
Oil, Coal Tar			A	A	A	-
Oil, Creosote, Sweet			A	A	A	-
Oil, Crude, Sweet	Cold		A	A	A	-
Oil, Diesel, #2D			A	A	A	-
Oil, Diesel, #3D			A	A	A	-
Oil, Diesel, #4D			A	A	A	-
Oil, Diesel, #5D			A	A	A	-
Oil, Essential			A	A	A	-
Oil, Fed. Spec. #10			A	A	A	-
Oil, Fed. Spec. #20			A	A	A	-
Oil, Fed. Spec. #30			A	A	A	-
Oil, Fed. Spec. #9170			A	A	A	-
Oil, Fed. Spec. #9250			A	A	A	-
Oil, Fed. Spec. #9370			A	A	A	-
Oil, Fed. Spec. #9500			A	A	A	-
Oil, Fed. Spec. SAE 20			A	A	A	-
Oil, Fed. Spec. SAE 30			A	A	A	-
Oil, Fed. Spec. SAE 40			A	A	A	-
Oil, Fed. Spec. SAE 50			A	A	A	-
Oil, Fed. Spec. SAE 60			A	A	A	-
Oil, Fed. Spec. SAE 70			A	A	A	-
Oil, Fed. Spec. SAE 90			A	A	A	-
Oil, Fed. Spec. SAE 140			A	A	A	-
Oil, Fed. Spec. SAE 250			A	A	A	-
Oil, Fuel #1			A	A	A	-
Oil, Fuel #2			A	A	A	-
Oil, Fuel #3			A	A	A	-
Oil, Fuel #5A			A	A	A	-

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:
Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Oil, Fuel #5B			A	A	A	–
Oil, Fuel #6			A	A	A	–
Oil, Insulating			A	A	A	–
Oil, Kerosene			A	A	A	–
Oil, Lean			A	A	A	–
Oil, Linseed (Raw)			A	A	A	–
Oil, Lubricating #8			A	A	A	–
Oil, Lubricating Diesel #9110			A	A	A	–
Oil, Mineral Lard Cutting, Fed Spec. #1			A	A	A	–
Oil, Mineral Lard Cutting, Fed Spec. #2			A	A	A	–
Oil, Mineral SAE 10			A	A	A	B
Oil, Navy Spec., Navyll			A	A	A	–
Oil, Quenching			A	A	A	–
Oil, Rich			A	A	A	–
Oil, Turbine Lube			A	A	A	–
Oil, Vegetable, Castor			A	A	A	–
Oil, Vegetable, China Wood			A	A	A	–
Oil, Vegetable, Coconut			A	A	A	–
Oil, Vegetable, Corn			A	A	A	–
Oil, Vegetable, Cottonseed			A	A	A	–
Oil, Vegetable, Linseed (Raw)			A	A	A	–
Oil, Vegetable, Olive			A	A	A	–
Oil, Vegetable, Palm			A	A	A	–
Oil, Vegetable, Peanut			A	A	A	–
Oil, Vegetable, Rape Seed			A	A	A	–
Oil, Vegetable, Rosin			A	A	A	–
Oil, Vegetable, Sesame			A	A	A	–
Oil, Vegetable, Soya Bean			A	A	A	–
Olefin, Crude			A	A	A	–
Oleic Acid			A	A	A	C
Oleums			C	C	C	C
Ortho-Phosphoric Acid	<80	All	A	–	–	–
Orthodichloro Benzene			A	A	–	–
OS 45 Type IV			B	B	B	–
Oxalic Acid (Ethanedioic Acid)	Cold		A	A	A	A (at 200F)
Oxalic Acid (Ethanedioic Acid)	Hot		A	A	A	–
Oxygen, Gas (<2000 psi)	<400	100	A	A	–	B
Oxygen, Liquid			A	A	–	A
Palmitic Acid (Hexadecanoic Acid)			A	A	A	A (at 150F)
Palmitic Acid, Stearic			A	B	A	–
Paracymene			A	A	A	–
Paradichlorobenzene		100	A	–	–	–
Paraffin, Liquid			A	A	A	–
Paraldehyde		100	A	–	–	–
Parkerizing Solution			A	–	–	–
Pectin, Liquor			A	A	A	–
Penicillin, Liquid			A	A	A	–
Pentachlorophenol			A	A	A	–

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Pentane			A	A	A	–
Pentasol			A	–	–	–
Perchloroethylene			A	A	A	C
Peroxide of Hydrogen	Cold	>90	C	C	C	C
Petrolatum			A	A	A	–
Petroleum Ether			A	A	A	A (at 150F)
Phenol (Carbolic Acid)	205	All	A	A	A	C
Phenol, Formaldehyde Mix			A	A	B	–
Phenyl Acetic Acid			A	A	A	–
Phidolene			A	–	–	–
Phosgene Gas			A	C	A	–
Phosphoric Acid	50	>40	A	B	A	A (at 200F)
Phosphoric Acid	Cold	100	A	A	A	–
Phosphoric Acid	<80	<45	A	B	A	A (at 200F)
Phosphoric Acid	Cold	<45	A	B	A	A (at 200F)
Phosphorus Trichloride (Dry)		100	A	A	A	A (at 200F)
Photographic Developers			A	A	B	A
Phthalic Anhydride (Anhydrous)			A	A	A	–
Phthalic Esters			A	A	–	–
Picric Acid, Molten			A	B	B	C
Picric Acid, Water Solution	<20		A	B	B	C
Plasticizer			A	A	A	–
Plating Solutions, Chrome	<22		A	C	C	–
Plating Solutions, Others			A	C	B	–
Poly Glycols			A	A	A	–
Polyphenyl Ether			–	–	–	–
Poly Vinyl Acetate			A	–	–	–
Potash (Plant Liquor)			A	B	B	–
Potash Alum (Aqueous)			A	A	–	–
Potash Sulfide			A	A	–	–
Potassium Bicarbonate			A	B	B	A (at 200F)
Potassium Bichromate (Aqueous)			B	B	–	B
Potassium Bromide			A	B	B	C
Potassium Carbonate (Aqueous)			A	A	B	C
Potassium Chlorate			A	B	B	A (at 70F)
Potassium Chloride (Aqueous) (Sylvite)			A	A	A	A (at 150F)
Potassium Cyanides (Aqueous)			A	A	B	–
Potassium Dichromate			B	B	B	A (at 150F)
Potassium Hydroxide (Aqueous)		>50	A	B	B	C
Potassium Hydroxide (Aqueous)		<50	A	B	A	C
Potassium, Molten			C	C	C	C
Potassium Nitrate (Aqueous)(Saltpeter)			B	B	B	B
Potassium Perfluoro Acetate			A	A	A	–
Potassium Permanganate			A	A	A	A (20%, 200F)
Potassium Phosphate (Di, Tri)			A	A	A	–
Potassium Sulfate (Aqueous)(Arcanite)			A	A	B	A (at 70F)
Propane (Dimethylmethane)			A	A	A	C
Propiolactone, beta	20		A	A	–	–

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:
Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Propionaldehyde			A	A	–	–
Propylene (Propane)			A	A	A	C
Propylene Glycol			A	A	A	B
Propylene Glycol & Water			A	–	–	–
Propylene Oxide			A	A	–	–
Pulp Stock			A	–	–	–
PVC, Liquid	230-260		A	–	–	–
Pyridine			A	A	A	C
Pyrogallic Acid			A	–	–	–
Pyroigneous Acid			A	A	–	–
Quick Clean (Tetrachloroethylene & Carbon Dioxide)			A	B	B	–
Raffinate			A	A	–	–
Rosin	38		A	A	A	–
Sal Ammoniac (Ammonium Chloride)			A	A	A	–
Salt Cake			A	A	A	–
Salt Cake (Aqueous)			A	A	A	–
Salt Water			A	B	A	A
Sea Water			A	A	A	A
Selenic Acid			A	–	–	A
Sewage			A	B	A	A
Shellac			A	A	A	–
Silicone Oils and Greases			A	A	–	–
Silver Nitrate		10	A	A	A	A
Skydol 500			A	A	A	–
Skydol 7000			A	A	A	–
Slop, Brewery			A	–	–	–
Slop, Distillers			A	–	–	–
Soap, Liquors			A	A	–	–
Soap, Solutions			A	A	A	A
Soda Ash (Sodium Carbonate)	Cold		B	B	B	–
Sodium, Molten	<450		A	–	–	–
Sodium Acetate			A	A	C	A (at 200F)
Sodium Aluminate			A	A	B	–
Sodium Bicarbonate (Aqueous)			A	A	A	A (at 100F)
Sodium Bisulfate			A	A	B	A (at 200F)
Sodium Bisulfite			A	A	A	A (at 200F)
Sodium Borate (Borax)			A	A	A	A (at 70F)
Sodium Carbonate (Aqueous)			B	B	B	B
Sodium Chlorate (Sat'd)			B	B	B	B
Sodium Chloride Sol. (Common Salt)		100	A	C	A	A (at 250F)
Sodium Chlorite	<22	0-4	A	–	–	–
Sodium Cyanamide			A	A	–	–
Sodium Cyanide (Aqueous)			B	B	B	B
Sodium Hydrosulfite			A	A	A	–
Sodium Hydroxide	<120	All	A	–	–	B
Sodium Hydroxide (Aqueous)	<65	<50	A	B	B	B
Sodium Hypochlorite	<22	20	A	B	A	A (at 70F)
Sodium Metaphosphate			B	B	B	–

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Sodium Metasilicate			A	A	A	–
Sodium Nitrate (Aqueous)(Soda Niter)			A	A	B	A (at 200F)
Sodium Perborate			A	B	B	–
Sodium Peroxide Sol.			A	A	B	A
Sodium Phosphate, Meta (Aqueous)			A	A	A	–
Sodium Phosphate, Mono (Aqueous)			A	A	A	–
Sodium Phosphate, Dibasic (Aqueous)			A	A	A	–
Sodium Phosphate, Tribasic (Aqueous)			A	A	A	–
Sodium Plumbite (Aqueous)			A	A	–	–
Sodium Silicate (Aqueous)(Water Glass)			A	A	A	–
Sodium Sulfate (Aqueous)(Glauber's Salt)			A	A	A	A (at 200F)
Sodium Sulfide			A	A	A	B
Sodium Sulfite (Aqueous)			C	C	C	C
Sodium Tetraborate			A	A	A	–
Sodium Thiosulfate			A	A	A	–
Solvasol 1,2, &3			A	A	A	–
Solvasol 73, 74			A	A	A	–
Sorbitol			A	A	–	–
Stannic Chloride			A	C	B	A (at 150F)
Starch			A	A	A	A
Steam	>120		A	A	A	A
Stearic Acid (Octodecanoic Acid)			A	A	–	A
Stearic and Oleic Acid			A	A	–	–
Stoddard Solvent			A	A	A	B
Strontium Nitrate (Aqueous)			A	–	–	–
Styrene (Monomer) (Vinylbenzene)			A	A	A	–
Succinic Acid			A	–	–	A (at 200F)
Sugar (Aqueous)			A	A	A	–
Sulfate Liquors			A	A	A	–
Sulfate of Lime			A	–	–	–
Sulfide of Hydrogen	<700		A	A	A	–
Sulfide of Sodium	Hot		A	C	B	–
Sulfide of Sodium	Cold		A	C	B	–
Sulfite Pulp			A	–	–	–
Sulfonic Acid	60	Dilute	–	–	–	–
Sulfur Chloride (Aqueous)	Cold		A	C	–	C
Sulfur Dioxide (Dry)			B	B	B	B
Sulfur Dioxide (Wet)			A	C	A	B
Sulfur Dioxide & Water			A	C	A	B
Sulfur in Water			B	–	–	–
Sulfur, Molten			B	B	C	B
Sulfur Monochloride		100	A	–	–	–
Sulfur Trioxide (Dry)			B	B	B	C
Sulfur Trioxide (Wet)			B	B	–	C
Sulfuric Acid	Cold	<70	A	C	A	C
Sulfuric Acid	<120	<60	A	C	B	C
Sulfuric Acid	<65	<95	A	C	A	B
Sulfuric Acid		>95	C	C	C	C

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Sulfuric Acid	<75	<10	A	C	A	A
Sulfuric Acid Fuming (Oleum)	Cold	20-25	C	C	C	C
Sulfurous Acid, Wet	Any	All	A	C	A	A
Sulphonated Fatty Alcohol			A	A	A	–
Sulphonated Vegetable Oils			A	A	A	–
Sulphuric Chlorohydrin			A	C	–	–
Syrup, (Sucrose Soln.)			A	A	A	–
Tall Oil	95		A	B	A	–
Tallow			A	A	A	B
Tannic Acid	<65		A	A	A	A (at 150F)
Tanning Liquors			A	A	A	A
Tar & Ammonia w/Water			A	A	A	–
Tar, Bituminous			A	A	A	–
Tar, Pine			A	A	A	–
Tartaric Acid, Aqueous	Hot		A	A	A	A (at 150F)
TBA (Tertiary Butyl Alcohol)			A	–	–	–
Terephthalic Acid			A	A	–	–
Tetrachloroethane		100	A	A	A	C
Tetrachloroethylene			A	A	–	A (at 200F)
Tetra Ethyl Lead			A	A	–	–
Tetrahydrofuran			B	B	B	C
Tetraphenyl			A	A	–	–
Therminol #1, 2, & 3			A	A	A	–
Titanium Tetrachloride			A	A	–	C
Toluene (Toluol) (Methylbenzene)			A	A	A	A (at 167F)
Tomato Pulp			A	A	A	–
Toxaphene			A	–	A	–
Trichlorobenzene			A	A	A	–
Trichloroethane (Dry)			A	A	A	–
Trichloroethane (wet)			A	–	A	–
Trichloroethylene (Dry)			A	A	A	A (at 167F)
Trichloroethylene (Wet)			A	A	A	A (at 167F)
Trichloronitromethane			A	A	–	–
Tricresyl Phosphate			A	A	A	A (at 167F)
Triethylamine			A	A	A	–
Triethylene			A	–	–	–
Triethylene Glycol Ethyl Ether			A	–	–	–
Trifluorovinylchloride			A	A	A	–
Trimethyl Amine			A	–	–	–
Trisodium Phosphate			A	A	A	A (at 70F)
Turpentine			A	A	A	C
UCON Heat Transfer Fluid (All Types)		100	A	–	–	–
Urea (Anhydrous) (Carbamide)	All	100	A	A	B	A (at 70F)
Urea (Wet) (Carbamide)	All	All	A	A	B	A (at 70F)
Urea & Phenolic Resins			A	–	–	–
Urine			A	A	A	A
Varnish, Aromatic			A	A	A	–
Varnish, Non-aromatic			A	A	A	–

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:
Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Medium	Temperature + Concentration		Garlock Graph-Lock® Style Numbers			
			3120 3123/3125	3124/3126 3125SS 3125TC 3128	3125HC (H276)	3125MC (Mylar- polyester)
	°C	%				
Vegetable Juice			A	A	A	–
Vetrocoke Solution (Wet)			A	A	A	–
Vinegar			A	A	A	A (at 150F)
Vinyl Chloride (Chloroethene)			A	A	A	–
Vinylidene Chloride			A	A	A	–
Vinyl Pyridine			A	A	A	–
Vitriole, White			B	B	B	–
Water, Boiler Feed			A	A	A	A
Water, Borated	Any		A	–	–	–
Water, Brackish			A	A	A	A
Water, Clean untreated			A	A	A	A
Water, Cooling Tower			A	A	A	A
Water, Condensate			A	A	A	A
Water, Distilled			A	A	A	A
Waterflood Service			A	A	A	–
Water, Fresh			A	A	A	A
Water, Heavy			A	A	A	–
Water, Hot	<135		A	A	A	A
Water, Mine			A	A	A	A
Water, River			A	A	A	A
Water, Salt & Sea, Solution			A	B	A	A
Water, Soapy	<100		A	A	A	A
Water w/Sol. Oil			A	A	A	–
Whiskey			A	A	A	B
White Liquor			A	A	A	–
White Water, Paper Mill			A	A	A	–
Wine			A	A	A	B
Wood Pulp (Stock)			A	–	–	–
Wood Vinegar			A	A	–	–
Wort (Beer Wort)			A	A	A	–
Xylene (Dimethylbenzene)			A	A	A	B
Yeast			A	–	–	A
Zeolite Treated Water			A	A	A	–
Zinc Ammonium Chloride			A	–	–	–
Zinc Chloride (Wet)			A	B	B	A (at 200F)
Zinc Chloride (Dry)			A	B	B	A (at 200F)
Zinc Cyanide			A	A	A	–
Zinc Nitrate			A	A	A	A (at 150F)
Zinc Phosphate			A	–	–	–
Zinc Sulfate			A	A	A	A (at 250F)

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:
Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.